



E-Screen 10%

Specifications

Product Type Interior/Transparent **Width** 78" (200cm), 98.4" (250cm), 122" (310cm)

Composition 36% Fiberglass/64% Vinyl **Weight** 10.3 oz/yd² (350g/m²) ± 5%

Breaking Strength Warp > 290 / Weft > 280 (lbs) **Thickness** .022" (0.55mm) ± 5%

Standard Packaging Rolls of 30 ly (27 lm) **Yarn Count** Warp/56 Weft/38 (ends per inch)

Specifications

Product Type	Interior/Transparent	Width	78" (200cm), 98.4" (250cm), 122" (310cm)
Composition	36% Fiberglass/64% Vinyl	Weight	10.3 oz/yd ² (350g/m ²) ± 5%
Breaking Strength	Warp > 290 / Weft > 280 (lbs)	Thickness	.022" (0.55mm) ± 5%
Standard Packaging	Rolls of 30 ly (27 lm)	Yarn Count	Warp/56 Weft/38 (ends per inch)

Fenestration Properties

Openess Factor* 10% **UV Blockage: Between 90% - 91%**

Number	Description	Ts	Rs	As	Tv	SC (Internal)	
						¼" CI	¼" HA
0202	White/White	30	57	13	23	0.43	0.37
0207	White/Pearl	24	47	29	20	0.48	0.39
0220	White/Linen	28	53	19	22	0.45	0.38
0707	Pearl/Pearl	26	32	42	20	0.57	0.45
0720	Pearl/Linen	24	39	37	19	0.53	0.42
2020	Linen/Linen	24	48	28	19	0.47	0.39
2022	Linen/Stone	31	43	26	23	0.52	0.42
3001	Charcoal/Grey	10	8	82	12	0.68	0.50
3006	Charcoal/Bronze	13	5	82	14	0.71	0.52
3030	Charcoal/Charcoal	11	4	85	12	0.71	0.52

Applications:



Applications:



Roller
Shades



Roman
Shades



Panel
Tracks



Verticals



Skylight
Blinds



Tensile
Structures

Fire Classifications: NFPA 701-99 TM#1, California U.S. Title 19

Fabrication Methods:

- Cutting: Cold cut, ultrasonic, crush cut or laser
- Seaming/Hemming: Thermal, high frequency, ultrasonic or sewing

Care and Cleaning: Remove dust with vacuum cleaner or compressed air. Do not scrub. Do not use solvents or any abrasive substance which might damage the coating of the fabric. Clean with a sponge or a soft brush dipped in soapy water using mild detergent*. Rinse with clean water. Leave the blind down until completely dry.

* You can also very gently rub the fabric with a clean white pencil eraser to remove small stains.



Roller Roman Panel Skylight Tensile Shades Shades Tracks Verticals Blinds Structures

Fire Classifications: NFPA 701-99 TM#1, California U.S. Title 19

Fabrication Methods:

- . Cutting: Cold cut, ultrasonic, crush cut or laser
- . Seaming/Hemming: Thermal, high frequency, ultrasonic or sewing

Care and Cleaning: Remove dust with vacuum cleaner or compressed air. Do not scrub. Do not use solvents or any abrasive substance which might damage the coating of the fabric. Clean with a sponge or a soft brush dipped in soapy water using mild detergent*. Rinse with clean water. Leave the blind down until completely dry.

* You can also very gently rub the fabric with a clean white pencil eraser to remove small stains.

* Please note that the Openness Factor is an approximation and may vary from color to color in the same fabric due to the color and manufacturing process.

The fenestration property tests were conducted by Matrix, Inc. at its Mesa, AZ solar laboratory. The samples were tested in accordance with ASHRAE Standard 74-1988 "Methods of Solar-Optical Properties of Materials." The solar transmittance (Ts), solar reflectance (Rs), solar absorptance (As), visible light transmittance (Tv) and Openness Factor (OF) were determined for the fabric alone. The Shading Coefficients (SC) were determined for the fabric used with a 1/4" clear plate and a 1/4" heat (H.A.) plate. The Shading Coefficients are for the fabric hung internally unless otherwise indicated. The Ts, Rs, As and Tv are expressed as percentages. The data and calculated results are presented in the above table.