



Satine

Specifications

Product Type Exterior/Interior Transparent **Width** 98.4" (250cm)

Composition 42% Fiberglass/58% Vinyl **Weight** 15.8 oz/yd² (535 g/m²) ± 5%

Breaking Strength Warp > 290 / Weft > 280 (lbs) **Thickness** .030" (0.78mm) ± 5%

Standard Packaging Rolls of 55 ly (50 lm) **Yarn Count** Warp/46 Weft/36 (ends per inch)

Specifications

Product Type	Exterior/Interior Transparent	Width	98.4" (250cm)
Composition	42% Fiberglass/58% Vinyl	Weight	15.8 oz/yd ² (535 g/m ²) ± 5%
Breaking Strength	Warp > 290 / Weft > 280 (lbs)	Thickness	.030" (0.78mm) ± 5%
Standard Packaging	Rolls of 55 ly (50 lm)	Yarn Count	Warp/46 Weft/36 (ends per inch)

Fenestration Properties

Openess Factor* 5% UV Blockage: Between 94% - 96%

Number	Description	Ts	Rs	As	Tv	SC (External)		SC (Internal)	
						1/4" CI	1/4" HA	1/4" CI	1/4" HA
0202	White/White	27	59	14	19	0.24	0.22	0.37	0.34
0207	White/Pearl Dark Side	13	52	35	10	0.17	0.16	0.42	0.36
		13	45	42	10	0.18	0.17	0.46	0.39
0606	Bronze/Bronze	9	7	84	10	0.19	0.18	0.69	0.51
1001	Sable/Grey Dark Side	6	26	68	6	0.16	0.15	0.57	0.44
		6	20	74	6	0.16	0.16	0.60	0.46
1002	Sable/White Dark Side	18	47	35	15	0.22	0.21	0.46	0.39
		18	43	39	15	0.23	0.21	0.49	0.40
1006	Sable/Bronze Dark Side	7	28	65	7	0.15	0.14	0.56	0.44
		7	21	72	7	0.15	0.15	0.60	0.47
2020	Linen/Linen	20	53	27	16	0.24	0.22	0.43	0.37
3001	Charcoal/Grey Dark Side	5	11	84	5	0.16	0.15	0.65	0.49
		5	9	86	5	0.16	0.16	0.67	0.49
3006	Charcoal/Bronze Dark Side	7	7	86	10	0.16	0.16	0.68	0.50
		7	6	87	10	0.16	0.16	0.69	0.51
3030	Charcoal/Charcoal	5	4	90	6	0.15	0.15	0.69	0.51

Applications:



Roller Shades



Roman Shades



Panel Tracks



Skylight Blinds



Tensile Structures

Fire Classifications: NFPA 701-99 TM#1, California U.S. Title 19, ASTM E 84-97a Class A

Fabrication Methods:

- Cutting: Cold cut, ultrasonic, crush cut or laser
- Seaming/Hemming: Thermal, high frequency, ultrasonic or sewing

Care and Cleaning: Remove dust with vacuum cleaner or compressed air. Do not scrub. Do not use solvents or any abrasive substance which might damage the coating of the fabric. Clean with a sponge or a soft brush dipped in soapy water using mild detergent*. Rinse with clean water. Leave the blind down until completely dry.

* You can also very gently rub the fabric with a clean white pencil eraser to remove small stains.

Ap

Applications:



Roller Roman Panel Skylight Tensile Shades Shades Tracks Blinds Structures

Fire Classifications: NFPA 701-99 TM#1, California U.S. Title 19, ASTM E 84-97a Class A

Fabrication Methods:

- . Cutting: Cold cut, ultrasonic, crush cut or laser
- . Seaming/Hemming: Thermal, high frequency, ultrasonic or sewing

Care and Cleaning: Remove dust with vacuum cleaner or compressed air. Do not scrub. Do not use solvents or any abrasive substance which might damage the coating of the fabric. Clean with a sponge or a soft brush dipped in soapy water using mild detergent*. Rinse with clean water. Leave the blind down until completely dry.

* You can also very gently rub the fabric with a clean white pencil eraser to remove small stains.

* Please note that the Openness Factor is an approximation and may vary from color to color in the same fabric due to the color and manufacturing process. The fenestration property tests were conducted by Matrix, Inc. at its Mesa, AZ solar laboratory. The samples were tested in accordance with ASHRAE Standard 74-1988 "Methods of Solar-Optical Properties of Materials." The solar transmittance (Ts), solar reflectance (Rs), solar absorptance (As), visible light transmittance (Tv) and Openness Factor (OF) were determined for the fabric alone. The Shading Coefficients (SC) were determined for the fabric used with a 1/4" clear plate and a 1/4" heat (H.A.) plate. The Shading Coefficients are for the fabric hung internally unless otherwise indicated. The Ts, Rs, As and Tv are expressed as percentages. The data and calculated results are presented in the above table.